

Epoxy Accelerator

To Improve Cure Rate of Selected Epoxy Coatings.

FEATURES		RECOMMENDED USES	
<p>Advantages:</p> <ul style="list-style-type: none"> Accelerates cure of treated epoxy coatings at low temperatures Cure and recoat times may be reduced by as much as 50% Reduces time to touch dry / dust free Reduce shop turn-around times in less than ideal conditions Reduce time to mask out prior to topcoating <p>For further information, consult Altex Coatings Technical Services Dept.</p>		<p>Epoxy Accelerator is designed for use in epoxy coatings to reduce cure times at low temperatures:</p> <p>Limitations of Use:</p> <ul style="list-style-type: none"> The use of accelerators or force curing may shorten the aged recoat of individual coatings The use of accelerators will shorten the mixed pot-life of individual coatings The use of this accelerator may compromise the sanding properties of Altex Barrier Undercoat. Do not leave for extended periods, nor over accelerate. <p>Epoxy Accelerator should only be used to <i>accelerate</i> the cure of coatings under adverse conditions; <u>it is not a means by which to lower the absolute cure temperature of an individual coating</u> - such misuse of Epoxy Accelerator will result in marginal true cure and possible β-phasing of the epoxy polymer reaction.</p>	
SPECIFICATION DATA			
<p>Product Type: Amine Additive</p> <p>Colours: Amber</p> <p>Packaging: NZ & Aust: 500ml Single component additive</p> <p>Mix Ratio: See Overleaf</p> <p>Flash Point: 115°C Setaflash</p> <p>Storage: Store under cool, dry conditions</p>	<p>Density: 0.97 kg per litre</p> <p>Volume Solids: 100%</p> <p>Induction Time: 15 minutes at 10°C</p> <p>Dose Rates: Up to 25 mls of Accelerator per 1 Litre of MIXED product.</p>		

DIRECTIONS FOR USE

Use up to 25mls of Epoxy Accelerator per litre of mixed product.

- Add to mixed product before adding any thinner.
- Epoxy Accelerator must be mixed in thoroughly.
- At 10°C, a 15 minutes induction time is required once added to the mixed product.

MIXING:

Mix the base and converter at the appropriate mix ratio, add the required amount of accelerator while continuing to mix the product.

Thoroughly mix the solution for at least 5 minutes. Allow to stand (induct) for 15 minutes (minimum) prior to thinning (if required) and application

For additional information / advice, please contact the Altex Technical Support Helpline.

Limitations of Use:

- The use of Epoxy Accelerator will reduce the overall maximum self recoat and overcoating times for all treated products.
- The use of accelerators will shorten the mixed pot-life of individual coatings by approximately 50% at recommended dosing rates.
- Do not use in coatings with a pot life of 60 minutes or less.
- The use of this accelerator may compromise the sanding properties of Altex Barrier Undercoat. Do not leave for extended periods, nor over accelerate.

PRECAUTIONS

For industrial use only: Read and follow all the caution statements on this Product Data Sheet, the product label and the Safety Data Sheet (SDS) for health and safety information prior to use.

Epoxy Accelerator is flammable. Keep away from heat, sparks and open flame. Use with adequate ventilation. May cause eye and skin irritation. Do not breathe vapour or spray. Wear suitable protective clothing such as gloves and eye and face protection.

WWW.ALTEXCOATINGS.COM

**Head Office New Zealand
Altex Coatings Ltd**
91-111 Oropi Road
Greerton, Tauranga 3112
Ph : +64 7 541 1221
Fax : +64 7 541 1310

**Head Office Australia
Resene Paints (Aust) Ltd
Industrial & Marine Division**
7 Production Avenue, Molendinar
Queensland 4214
Ph : +61 7 5512 600
Fax : +61 7 5512 697

DISCLAIMER

The information in this datasheet is provided as a guide only and is provided without warranty, implied or otherwise. It is your responsibility to determine the suitability of any information or product for the use contemplated. Conditions of use, application and the substrate are beyond our control so no liability whatsoever (whether as to coverage, performance, injury or otherwise) is accepted for the information contained herein.
Data sheets may change from time to time and it is your responsibility to ensure you have the latest product datasheet and material safety data sheet from your supplier. Check the data sheet date with the listings at www.altexcoatings.com
Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.