

SELECTION & SPECIFICATION DATA

| | |
|----------------------------------|--|
| Generic Type | Amine-adduct cured epoxy |
| Description | This product is a solvent-free, high performance epoxy coating specifically designed as a pit filling primer with ideal flow properties allowing it to wet-out and fill moderate to severe pitting on steel tank bottoms. It's unique formula allows batch mixing for ease of application. Plural component spray equipment is not required. With an appropriate lining, it can withstand exposures typically seen in the oil and gas industries. It is resistant to crude oil, NGL condensates, produced water, brines, and industrial process water. |
| Features | <ul style="list-style-type: none"> • Highly penetrating formula to handle severe pitting • Blast hold protection • Batch mix formulation, single leg airless spray. • Superior adhesion to steel • Excellent abrasion resistance and flexibility • Can be applied down to 2°C • Can be used with multiple lining systems • Non-blushing with a long recoat window • Convenient packaging for batch mix • Low odour |
| Colour | Standard: Manilla (0200) |
| Primer | Self-priming. |
| Dry Film Thickness | 76 - 127 microns (3 - 5 mils) minimum, non pitted surface For moderate to severely pitted steel tank bottoms apply as needed to fill and seal pits. |
| Solids Content | By Volume 98% +/- 2% |
| Theoretical Coverage Rate | 38.6 m ² at 25 microns (1572 ft ² at 1.0 mils) 12.9 m ² at 75 microns (524 ft ² at 3.0 mils) 7.7 m ² at 125 microns (314 ft ² at 5.0 mils) Allow for loss in mixing and application. |
| VOC Values | As Supplied : 4 g/l |
| Wet Temp. Resistance | Immersion temperature resistance depends upon exposure, consult Carboline Technical Service for specific information |

SUBSTRATES & SURFACE PREPARATION

| | |
|----------------|---|
| General | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating |
| Steel | Cleanliness: Abrasive blast to SSPC-SP10 (AS1627.4 Class 2.5) (minimum) Profile: Minimum 75 micron dense, sharp anchor profile free of peening, as measured by ASTM D4417. Defects exposed by blasting must be repaired. Use appropriate abrasive mix to clean pit depressions. |

Phenoline Tank Shield FP

PRODUCT DATA SHEET



SUBSTRATES & SURFACE PREPARATION

Concrete | Concrete: Clean and dry. Remove all loose, unsound concrete. Do not apply coating unless concrete has cured at least 28 days @ 21°C and 50% RH or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete may require filling/surfacing.

MIXING & THINNING

Mixing | This product may be batch mixed and applied using standard airless spray equipment. Combine and power mix until homogeneous.

Component Details:
Manilla (0200): The Part A is yellow and Part B is white.

Thinning | Thinning not normally required. CLEANUP THINNER: Thinner #2 or #76.

Ratio | 1:1 by volume (Part A to Part B)

Pot Life | 30 minutes @ 24°C material temperature and less at higher temperatures. Storage in a cool location will aid with pot life. This product will exotherm (heat up) in large containers and shorten pot life. Mix only what you can apply within the pot life. The 4 gal. kits are packaged for simple and fast mixing with extra space in the Part A container for the B to be incorporated.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

General | This is a high solids coating and may require adjustments in spray techniques. The following spray equipment has been found suitable and is widely available.

Airless Spray | Airless spray equipment capable of minimum 5000 psi (55:1 ratio or larger). Fluid hose shall be minimum 1/2" I.D. with short 3/8" I.D. whip hose recommended. Airless spray gun shall be rated minimum 6000 psi utilizing reverse-a-clean tips sizes 0.017-0.027". Fixed-ratio (1:1 by volume) plural component equipment may also be used. For severely pitted steel surfaces, the use of a squeegee and/or back-rolling will aid in the complete coverage and treatment of pits. Consult Carboline Technical Service for details.

Roller | Phenoline Tank Shield FP may be poured and spread thin with short nap synthetic core rollers. Pour mixed material in ribbons to minimise placement time and maintain workability.

APPLICATION CONDITIONS

| Condition | Material | Surface | Ambient | Humidity |
|-----------|--------------|--------------|--------------|----------|
| Minimum | 13°C (55°F) | 2°C (35°F) | 2°C (35°F) | 0% |
| Maximum | 43°C (110°F) | 52°C (125°F) | 43°C (110°F) | 85% |

This product requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

CURING SCHEDULE

| Surface Temp. | Dry to Touch | Dry to Handle or Topcoat | Maximum Recoat Time |
|---------------|--------------|--------------------------|---------------------|
| 2°C (35°F) | 24 Hours | 30 Hours | 30 Days |
| 10°C (50°F) | 12 Hours | 14 Hours | 30 Days |
| 24°C (75°F) | 6 Hours | 7 Hours | 30 Days |
| 32°C (90°F) | 4 Hours | 4 Hours | 30 Days |

For recoating, if the product has exceeded the maximum recoat time, de-gloss and roughen by sanding or mechanically abrade the surface and remove dust prior to topcoating.

CLEANUP & SAFETY

Cleanup | Thinner #2 or #76 are recommended for clean up.

Safety | Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions.

Ventilation | When used as a tank lining or in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. In addition to ensuring proper ventilation, appropriate respirators must be used by all application personnel.

PACKAGING, HANDLING & STORAGE

Shelf Life | 12 months

Shipping Weight (Approximate) | 5.5 kg/3.78 litres, (12 lbs/gal)

Storage Temperature & Humidity | 4°- 43°C
0-90% Relative Humidity

Flash Point (Setaflash) | Part A: 74°C
Part B: 95°C

Packaging | Available in 37.8-lit (10 gal), 15.1 lit (4-gal) and 7.5 lit (2 gal) kits.

WARRANTY

Manufactured and / or distributed in Australia & New Zealand by Altex Coatings under license to Carboline Company. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Altex Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ALTEX COATINGS OR CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.